



































































































Chemical Resistance Chart

-  Suitable for application
-  Soft Seal / Soft Seal HD suitable other materials dependent on conditions
-  Not suitable / consider graphite

Acetic Acid Glacial		Dichlorobenzene		Nitric Acid (95%)	
Acetone		Diesel Oil		Oxygen	
Acetylene		Dioxane		Paraffin	
Acrylic Acid		Ethyl Acetate		Perchloric Acid	
Acrylonitrile		Ethyl Alcohol		Petrol	
Air		Ethylene Glycol		Phenol	
Ammonia Gas		Ethylene Oxide		Phosgene	
Ammonia		Ethyl Ether		Phosphorous	
Amyl Acetate		Ethylene		Phthalic Anhydride	
Amyl Alcohol		Ethylene Chloride		Potassium Hydroxide	
Beer		Fluorine		Potassium Nitrate	
Benzene		Fluorosilicic Acid		Potassium Permanganate	
Benzoyl Chloride		Formaldehyde		Pyridine	
Biphenyl		Formic Acid (85%)		Sodium Bicarbonate	
Bromine		Formic Acid (10%)		Sodium Carbonate	
n-Butyl Acetate		Gasoline		Sodium Cyanide	
Caprolactam		Hydrochloric Acid (37%)		Sodium Hypochlorite	
Carbolic Acid		Hydrofluoric Acid		Sodium Nitrate	
Carbon Dioxide		Hydrogen		Steam	
Carbon Disulphide		Hydrogen Fluoride		Styrene	
Carbon Monoxide		Hydrogen Peroxide		Sulphur Dioxide	
Carbon Tetrachloride		Hydrogen Sulphide		Sulphur Trioxide	
Chlorine Dry		Isopropyl Alcohol		Sulphuric Acid	
Chlorine Wet		Kerosene		Toluene	
Chloroacetic Acid		Lubricating Oil		Transformer Oil (Mineral Type)	
Chlorobenzene		Magnesium Sulphate		Vegetable Oil	
Chromic Acid		Malic Acid		Vinyl Acetate	
Copper Sulphate		Methane		Vinyl Chloride	
Creosote		Methyl Alcohol		Water	
Cresol		Methyl Isobutyl Ketone		Water Distilled	
Crude Oil		Methylene Chloride		Wine	
Cyclohexanol		Nitric Acid (50%)		Xylene	