

PRODUCT SPECIFICATION SHEET

MATERIAL : WCL Superior

Non-asbestos jointing sheet, composed of kevlar® aramid fibres and high temperature resistant mineral fillers, bonded with high ACN-content NBR elastomer. The formulation gives the material excellent chemical stability and resistance to creep.

Applications

Universal use, gases, hydrocarbons, solvents, low pressure steam, mild acids and alkalis. Suitable for food industry, public utilities, water treatment plants, chemical plants, oil industry, etc.

Technical Data (values relate to 2 mm thickness)

Density	DIN 3754		1.75	g/cm ³
Service limits*:				
Max. short term temperature			370	°C
Max. continuous operating temperature with non-aggressive media			320	°C
Max. continuous operating temperature with steam			200	°C
Max. operating pressure			100	bar
Compressibility	ASTM F36		8	%
Recovery	ASTM F36	min.	50	%
Stress retention:				
- 16 hrs, 300 °C, 50 N/mm ²	DIN 52913	min.	26	N/mm ²
- 16 hrs, 175 °C, 50 N/mm ²		min.	38	N/mm ²
Tensile Strength (across grain)	DIN 52910	min.	12	N/mm ²
Gas permeability (N ₂ , 40 bar, 30 N/mm ² , 200°C)	DIN 28090	max.	0.05	mg/m.sec
Ignition loss	DIN 52911	max.	30	%
Immersion test in ASTM Oil 3 for 5 hrs. at 150°C				
- weight increase	ASTM F146	max.	10	%
- thickness increase		max.	5	%
Immersion test in ASTM Fuel B for 5 hrs at 20°C				
- weight increase	ASTM F146	max.	10	%
- thickness increase		max.	5	%
- tensile strength		min.	7	N/mm ²



Whitby and Chandler Ltd

Green Road
 Penistone
 Sheffield
 S36 6PH



Tel: +44 1226 370 380 Fax: +44 1226 767 138

E mail enquiries@whitby-chandler.co.uk

PRODUCT SPECIFICATION SHEET

MATERIAL : WCL Superior

Compression strength σ_{VO} at Room Temp.:	DIN 28090	min.	160	N/mm ²
" " " σ_{BO} at 100°C:	"	min.	75	N/mm ²
" " " σ_{BO} at 200°C:	"	min.	40	N/mm ²

* Max. temperature and pressure do not hold simultaneously and are reported for proper seating conditions and gasket design

Supply data

Surface color:	blue	Surface finishing:	upon request: 4xA Anti-stick coating
Sheet size - Standard:	1500 x 1500 mm (upon request: 1500x3000 and 1500x4500 mm)	tolerance:	+/- 50 mm
Thickness:	from 0.3 to 5.0 mm	tolerance:	+/- 10%

References: BS 7531 grade Y, DIN 28091 FA - A1 - 0

Joining manufacture is quality assured in accordance with ISO 9001

Data here reported, corresponding to laboratory and field tests results, are meant as non-binding guideline for gasket selection. No guarantee claim can be inferred from them. When needed, we shall be pleased to assist you with specific technical assistance.



Whitby and Chandler Ltd

Green Road
 Penistone
 Sheffield
 S36 6PH



Tel: +44 1226 370 380 Fax: +44 1226 767 138

E mail enquiries@whitby-chandler.co.uk